

EpoxyShield® Cleaner/Degreaser – 2901



Description

RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors is a concentrated, alkaline, non-flammable, virtually odour-free cleaning/degreasing solution.

Recommended Uses

RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors should be used to remove grease, oil, proteins dirt and many other surface contaminants from coated, mineral and steel substrates.

RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors should be applied with an artificial sponge, cloth or stiff nylon brush or broom.

RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors can also be used as an additive for high-pressure (steam) cleaning.

Technical Data

VOC-content: 9 g/l

Coverage

Theoretical: 6 - 8 m²/l

Practical: Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

Direction For Use

To ensure homogeneity shake well before use.

Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible.

RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors can be applied with a sponge, cloth, brush, and broom or cleaning machine. When used in combination with a cleaning machine dilute with 50% cold water. After use rinse with plenty of fresh water.

After cleaning, remove any remaining water and allow the surface to dry, as moisture left on the surface or entrapped into pores may cause premature failure of the coating system.

Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

Application Conditions

Temperature of air, substrate and material between 5 and 35°C.

Remarks

If used on galvanized steel, zinc, aluminium or anodized aluminium rinse the surface.

Safety

Consult Safety Data Sheet and Safety Information printed on the can.

Shelf Life / Storage Conditions

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

