

Hard Hat® Aerosols Marking Paint 2300



Description

RUST-OLEUM® Hard Hat Aerosol Marking Paint 2300 is based on a fast drying, short oil alkyd (2358 is based on an acrylic resin). The products are based on lead and chromate free pigments.

Recommended Uses

RUST-OLEUM Marking Paint 2300 should be used on metal, concrete, asphalt, gravel, soil and grass, etc.

RUST-OLEUM Marking Paint 2300 is not water-soluble and should be used in light industrial exposures, normal humidity and interior applications.

RUST-OLEUM Marking Paint 2300 is designed for quick and easy marking of construction and excavation sites, underground utilities and for traffic safety.

Technical Data

| | |
|------------------|--|
| Appearance: | Flat |
| Colour: | See colour card |
| Propellant: | Dimethyl ether |
| VOC-content: | 630 g/l |
| Drying times | 20°C/50% r.v. |
| To touch: | 20 minutes |
| To handle: | 4 hours |
| To recoat: | Within 1 hour or after 48 hours |
| Full hardness: | 7 days |
| Heat resistance: | 100°C (dry heat) |
| Coverage | |
| Theoretical: | 2m ² per spray can at 25µm dry, depending on colour. |
| Practical: | Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. |

Surface Preparation

Remove dirt, grease, oil and all other surface contaminants by appropriate means. The surface must be clean and dry during application.



Directions for Use

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing balls is heard. Shake frequently during use.

Invert can and point spray button at ground or floor. Hold can approximately 10-15 cm above the surface to be marked. Press spray button to start spraying. Use a steady even stroke while spraying.

After use turn can upright and press spray button for 2-3 seconds to clean valve.

Application Conditions

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

Remarks

Fluorescent Marking Paint should be applied on a white substrate for maximum brightness.

Safety

Consult Safety Data Sheet and Safety Information printed on the can.

Shelf Life / Storage Conditions

Three years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight, at temperatures between 5° and 35°C.